

University of Technology, Sydney

Faculty of Science

**A STUDY OF THIN-FOIL ROLLING
AND THE DEVELOPMENT OF AN Al-
Fe-Mn-Si LIGHT GAUGE FOIL ALLOY**

Part 1

Course: N054 Doctorate in Science – (by Thesis)

Author: Matthew Mansell

Supervisor: Dr. Greg Heness

2007



CERTIFICATE OF AUTHORSHIP/ORIGINALITY

I certify that the work presented in this thesis has not previously been submitted for a degree nor has it been submitted as part of requirements for a degree except as fully acknowledged within the text.

I also certify that the thesis has been written by me. Any help that I have received in my research work and the preparation of the thesis itself has been acknowledged. In addition, I certify that all information sources and literature used are indicated in the thesis.

Signature of Candidate

A. W. Mull

14th December 2006.

ACKNOWLEDGMENTS

I would like to thank the following people who have assisted in the production of this thesis:

IAS, in particular Tony Santino for assistance on modelling of thin film foils.

ALCOA AUSTRALIA ROLLED PRODUCTS for their support on this project.

Dr Greg Heness, who's assistance was essential in completing this thesis, and his support in upgrading from a masters to a doctorate in Applied Science.

Milt Milner, Rob Sanders Jr, Mike Ringle, Tom Rouns and other members of ATC for there assistance in analysing the microstructure.

Jennifer Russell, Paul Munro and members of the Department of Physics – UTS for their assistance with surface topography.

My wife Fiona, children Tamika and Jai - Your support and patience over the years has kept me going when I wanted to stop, and I dedicate this to you.

CONTENTS

CERTIFICATE OF AUTHORSHIP/ORIGINALITY.....	2
ACKNOWLEDGMENTS	3
CONTENTS	4
LIST OF FIGURES	9
LIST OF TABLES	14
ABSTRACT	15
CHAPTER 1 INTRODUCTION.....	16
1.1. World Growth - Export Overflow.....	16
1.2. Aluminium Foil: Innovations and Outlooks	18
1.3. Foil in Australia – Thesis Justification	21
LITERATURE SURVEY	24
CHAPTER 2 ALUMINIUM AND ITS ALLOYS.....	25
2.1. Introduction.....	25
2.2. Aluminium Designations	27
2.3. Foil Alloys.....	31
2.3.1. Aluminium – The Metal.....	32
2.3.2. 1xxx Alloys	33
2.3.2.1. The Effect of Individual Additions for Foil Alloys	35
2.3.2.2. Casting of Aluminium Alloys	38
2.3.2.3. Phases and Microstructure in 1xxx Alloys	47
2.3.2.4. Strengthening Mechanisms in Foil Alloys.....	51
2.3.2.5. Annealing of 1xxx Alloys	59
2.3.2.6. Surface Oxide Studies	61
2.3.3. 8XXX Alloys	67

CHAPTER 3	ROLLING THEORY	72
3.1.	Introduction.....	72
3.2.	Circular Arc Rolling Model (Orowan's Model)	75
3.2.1.	Asymptotic Techniques.....	80
3.2.2.	Finite Element Methods	80
3.3.	Non-Circular Arc Rolling Model	82
3.3.1.	Roll Pressure in the Plastic Region	83
3.3.2.	Roll Pressure in the Elastic Region.....	84
3.3.3.	Roll Deformation Model	85
3.3.4.	Yield Stress Model.....	88
3.3.5.	Temperature Model	88
3.3.6.	Initialisation and Convergence Algorithm	90
3.4.	Particle Break-Up Modelling	91
3.4.1.	Introduction - Particle Effects on Recrystallisation	91
3.4.2.	Particle Break-up Theory	93
3.4.2.1.	Log-Normal Distribution	95
3.4.2.2.	Fracture of Brittle Particles Theory.....	97
3.4.2.3.	Comminution Theory.....	99
3.4.2.4.	Model Development.....	99
CHAPTER 4	ROLLING LUBRICATION – TRIBOLOGY	102
4.1.	Functions of Lubrication.....	102
4.2.	Fundamentals in Metalworking.....	104
4.2.1.	Lubrication Regimes	107
4.3.	Rolling Lubricants.....	111
4.3.1.	Base Oils	111
4.3.2.	Lubricant Additions	113

4.4.	Batch versus Flash Annealing of Foil Alloys	116
4.5.	General Adhesion Principles - Stickiness	119
CHAPTER 5 WEB HANDLING		124
5.1.	Introduction	124
5.2.	Metal Dimensions	125
5.3.	Traction	128
5.3.1.	Air Entrapment.....	128
5.3.2.	Lubricant	129
5.4.	Tension.....	131
5.4.1.	Torque Capacity	132
5.4.2.	Torque Calculations	134
5.4.3.	Inertial effects (acceleration / deceleration).....	135
5.5.	Wrinkles / Creasing.....	137
5.5.1.	Non-Uniform Strip Elongation	139
5.5.1.1.	Shape	139
5.5.1.2.	Tension Buckling	140
5.5.1.3.	Ripple Collapse Producing Creasing	140
5.5.2.	Shape Issues	143
5.5.3.	Reducing Creasing through Mechanical Means	148
BENCHMARKING AND OPTIMISATION		151
CHAPTER 6 WEB FAILURE		152
6.1.	Miscellaneous Web Failures	153
6.1.1.	Casting Defects	153
6.1.2.	Rolling Defects.....	157
6.1.3.	Handling or Storage Defects	164
6.2.	Other Influences on Web Failure	166

6.2.1.	Effects of Boundary Lubrication on Web Failure.....	166
6.2.1.1.	Experimental	167
6.2.1.2.	Discussion - Development of the Mansell Curve	170
6.2.1.3.	Conclusion	173
6.2.2.	Effects of Entrained Polymers on Web Failure.....	174
6.2.2.1.	Experimental Procedure	174
6.2.2.2.	Results of the Investigation.....	175
6.2.2.3.	Discussion and Conclusion	178
6.2.3.	Filtration Methods for Foil - Web Failure	179
6.2.3.1.	Experimental Procedure	181
6.2.3.2.	Results and Discussion.....	183
6.2.3.3.	Conclusion	186
CHAPTER 7 STEADY-STATE VELOCITY VARIABLES		188
7.1.	Introduction.....	188
7.2.	Initial Settings	190
7.2.1.	Exit Tension / Stress	191
7.2.2.	Entry Tension / Stress	194
7.2.3.	Load.....	198
7.2.4.	Coolant Temperature / Viscosity	200
7.3.	Final Speed Settings.....	201
7.4.	Break Rate.....	204
7.5.	A Comparison between Chromed and Steel Work Rolls.....	205
7.5.1.	Chroming Process	206
7.5.2.	Speed changes	209
7.5.3.	Pinholes.....	209
7.5.4.	Conclusion	211

REFERENCES212

LIST OF FIGURES

Figure 1.1. Aluminium foil deliveries 1997-2004 to the EAFA	17
Figure 1.2. Foil domestic market 1980 - 89, 1997 - 2003	21
Figure 2.1. Primary aluminium production by region.....	26
Figure 2.2. Recent growth of aluminium production in the western world.....	26
Figure 2.3. Temper designations	30
Figure 2.4. Typical concentration of iron and silicon in foil alloys Al-Fe(Mn)-Si (1xxx, 8xxx), Al-Fe-Mn (8xxx).	31
Figure 2.5. Segregation effects in a 1xxx series alloy	36
Figure 2.6. Cake-mode filtration	41
Figure 2.7. Depth-mode filtration.....	41
Figure 2.8. Section of a CFF	42
Figure 2.9. Filter section of a RMF	43
Figure 2.10. Isochronal annealing curve for alloy 1100-H19	51
Figure 2.11. Typical burst strengths.....	52
Figure 2.12. Variation of yield strength with grain size.....	53
Figure 2.13. Volume fraction in 1xxx alloys.....	55
Figure 2.14. Schematic representation of Orowan looping.....	56
Figure 2.15. Cell dislocation cellular Structures	56
Figure 2.16. Effects of alloy additions on aging in aluminium, (a) atomic %; (b) weight %.....	58
Figure 2.17. Effects of alloy additions on UTS in aluminium	58
Figure 2.18. Effects of alloy additions on yield strength in aluminium	58
Figures 2.19 - 2.20. Cold work and time/temperature factors for 1XXX alloy	59
Figure 2.21. Schematic Model of Oxide Film Growth for Al-Mg Alloys.	63
Figure 2.22. SEM photos of foil surfaces 500x – bright side.....	65

Figure 2.23. SEM photos of foil surfaces 500x - matte side	65
Figure 2.24. Secondary ion mass spectroscopy of matte foil surface for 1145 alloy - free unwind.....	66
Figure 2.25. X-ray photoelectron spectroscopy of matte foil surface for 1145 alloy – sticky unwind	66
Figure 2.26. Aluminium - iron phase diagram	69
Figure 2.27. Aluminium – iron – silicon phase diagram	70
Figure 2.28. Aluminium – iron – manganese - silicon phase diagram	71
Figure 3.1. Major areas associated with flat rolling technology	72
Figure 3.2. Rolling regimes for different mill types.....	74
Figure 3.3. Slab-based rolling model	76
Figure 3.4. Roll gap geometry	76
Figure 3.5. Typical roll gap profile as predicted by the Fleck and Johnson model...	83
Figure 3.6. Jortner influence function normalised to have unit maximum	85
Figure 3.7. Pressure spike from roll flattening	87
Figure 3.8. Conditions of strain and particle size for which PSN occurs in an aluminium silicon alloy.....	93
Figure 3.9. Particle dimensions	96
Figure 4.1. Wilson – Walowitz equation.....	106
Figure 4.2. Stribeck curve.....	108
Figure 4.3. Modified Stribeck diagram	110
Figure 4.4. Variation of viscosity with temperature for mineral oils	112
Figure 4.5. Schematic illustration of the mode of action of a compound oil-based lubricant.....	115
Figure 4.6. Tensile strength versus temperature for flash annealing.....	116
Figure 4.7. Tensile strength versus thickness for flash annealing.....	116
Figure 4.8. Softening in aluminium - iron alloys, 8079 and IN30.	118

Figure 4.9. Grain size effect on bending and burst strength for 8079 and IN30.	118
Figure 4.10. Idealised time/temperature diagram from Dean and Hauser.....	121
Figure 4.11. Schematic for the development of coil stickiness and wettability	123
Figure 5.1. Web camber	126
Figure 5.2. Wedge and profile measurements	127
Figure 5.3. Ironing roll	128
Figure 5.4. COF collapse.....	130
Figure 5.5. Web tension.....	131
Figure 5.6. Torque capacity	132
Figure 5.7. Clockspring schematic	133
Figure 5.8. Torque calculations using the Capstan equation.....	135
Figure 5.9. Inertial effects – acceleration	136
Figure 5.10. Inertial effects – deceleration	136
Figure 5.11. Wrinkles on light film web	138
Figure 5.12. Stress distribution.....	139
Figure 5.13. Web rigidity	142
Figure 5.14. Wavy edges	143
Figure 5.15. Centre buckles.....	144
Figure 5.16. Quarter buckle.....	145
Figure 5.17. Hot spots	146
Figure 5.18. Hot buckling.....	147
Figure 5.19. Idler rolls	148
Figure 5.20. Herringbone roll	149
Figure 5.21. Curved roll	150
Figure 6.1. ‘Normal’ foil surface (x75)	168
Figure 6.2. Ladder defect (x75).....	169

Figure 6.3. Ladder defect (x200).....	169
Figure 6.4. Surface specimens at different rolling speeds.....	170
Figure 6.5. Specimen surface with penetrating lubricant pockets.....	171
Figure 6.6. Herringbone Defect.....	172
Figure 6.7. Mansell curve – film thickness versus film strength for 6.5µm 1145 foil.	173
Figure 6.8. Macrophoto of defect.....	175
Figure 6.9. FTIR finger print for black stain for samples (a) 6.5 micron and (b) 220 micron	176
Figure 6.10. EDAX analysis for the black stain on the 220 micron sample	177
Figure 6.11. Pinholes in light gauge foil	180
Figure 6.12. Light box used to calculated pinholes, (a) general (b) in use.....	182
Figure 6.13. Roll changes per year (a mevil is coil weight divided by the width in centimeters).....	183
Figure 6.14. Roll Change Frequency (all values are 6.5 micron 1145 product unless stated).	184
Figure 6.15. Break Rate Trials for 6.5µm 1145 foil.....	185
Figure 6.16. Pinhole Comparison between DBF and CCF Product.	186
Figure 7.1. Variation in speed with tension.....	189
Figure 7.2. Exit tension – breakdown pass.....	191
Figure 7.3. Exit stress – breakdown pass.....	192
Figure 7.4. Exit tension – final single.....	192
Figure 7.5. Exit stress – final single	193
Figure 7.6. Exit tension – double pass.....	193
Figure 7.7. Exit stress - double pass.....	194
Figure 7.8. Entry tension – breakdown pass.....	195
Figure 7.9. Entry stress – breakdown pass	195

Figure 7.10. Entry tension – final single	196
Figure 7.11. Entry stress – final single	196
Figure 7.12. Entry tension – doubling pass	197
Figure 7.13. Entry tension – doubling pass	197
Figure 7.14. Load – breakdown pass	198
Figure 7.15. Load – final single.....	199
Figure 7.16. Load - double pass	200
Figure 7.17. Speed increase with modified rolling parameters - 29 μ m	202
Figure 7.18. Speed increase with modified rolling parameters - 14 μ m	202
Figure 7.19. Speed increase with modified rolling parameters – 13D μ m.....	203
Figure 7.20. Speed versus breakrate relations – 13 μ m doubled product.....	204
Figure 7.21. Schematic of chrome nodules at work roll surface (80x)	206
Figure 7.22. Micro-finished surface of work roll (40x)	207
Figure 7.23. Final work roll finish at surface of work roll (40x)	208
Figure 7.24. Pinhole count for steel and chrome rolls.....	210

LIST OF TABLES

Table 1.1.	US aluminium foil shipments (including imports)	18
Table 2.1.	Designation system and precipitates for aluminium	28
Table 2.2.	Atomic and nuclear properties	32
Table 2.3.	Effect of purity on the properties of 1xxx alloys	34
Table 2.4.	Effect of small additions of chromium, titanium, zirconium on the properties of AA1050 100 micron foil.....	37
Table 2.5.	Impurity summary.....	38
Table 2.6.	Filtration efficiency.....	38
Table 2.7.	Inclusions in aluminium.....	40
Table 2.8.	Advantages/disadvantages of filtration types	44
Table 2.9.	Filtration summary.....	47
Table 2.10.	Phases present in 1xxx series alloys	49
Table 2.11.	Typical mechanical properties for various tempers and purities.	60
Table 2.12.	Mechanical properties of aluminium-iron alloys	68
Table 4.1.	Wilson - Walowitz variables.....	105
Table 4.2.	Addition film parameters	106
Table 5.1.	Effect of thickness.....	127
Table 6.1.	Typical pinhole variation with decreasing gauge.....	179
Table 6.2.	Process flow path	181
Table 6.3.	Predicted tangible and financial benefits of using DBF metal.....	187
Table 7.1.	Mill speed variables	189
Table 7.2.	Suggested rolling parameters – Foil Mill 2 Yennora.....	201
Table 7.3.	Effect of surface on rolling speed	209

ABSTRACT

There has been a trend in recent years to produce thinner but stronger thin-foil aluminium alloys at higher production velocities. This thesis discusses and examines product quality, rolling parameters, thermal treatment, web handling and alloy development in the context of the production of thin-foil aluminium products. The information is to be included in the ALCOA metallurgical database

Web failures are categorised and investigated over the life of the project. A short definition is provided followed by remedies to reduce or avoid re-occurrences. The effect of boundary lubrication between the metal and roll surfaces on web failure is summarized by the Mansell curve. The Mansell curve expresses rolling lubrication as a function of film strength and film thickness, and will be useful in determining rolling lubricant composition and temperature.

Optimal settings based on current rolling practices are determined for unwind tension/stress, lubricant viscosity, load and rewind tension/stress to achieve a consistent desired mill speed. The parameters are determined using existing rolling theory and are essential in maintaining production volume with decreasing gauge.

The improved stability of the process provides the foundation for trials on a new unique high strength alloy, AA8150 and accompanying process, developed and registered by the author. Alloy 8150 utilises a unique combination of high cold reduction, solid solution strengthening, constituent and dispersion strengthening to produce a fine grained structure with high strength and formability characteristics.

The wrought aluminium alloy 8150 contains iron, manganese and silicon at greater than 20% from the eutectic composition. High cold reduction with no intermediate thermal treatment results in highly misorientated random alignments in the deformation zone that surround large constituent particles, $\text{Al}_{12}(\text{FeMn})_3\text{Si}$ and $(\text{FeMn})\text{Al}_6$, making them effective recrystallisation nuclei sites. The $\text{Al}_{12}(\text{FeMn})_3\text{Si}$ and $\text{Al}_{12}(\text{MnFe})_3\text{Si}$ dispersoids/precipitates that occur during thermo-mechanical processing reduce the energy of the high angle boundaries, 'pinning' the boundary causing a new boundary to be formed as it curves around the particle, enhancing the nucleation of recrystallisation sites.